Heinrich-Held-Str. 33 \cdot 45133 Essen (Germany) Phone: +49(0)201/87225-0 \cdot Fax: +49(0)201/8722555 Email: info@coftech.de \cdot Internet: www.coftech.de

Black Lithium Niobate Wafer

(LiNbO3 Optical Grade)

When different types of ions are mixed into the LiNbO3 crystal, it exhibits various special properties, making it suitable for applications such as optical waveguide amplifiers, frequency-doubling converters, and optical storage media.

For example, in high-power laser applications, magnesium oxide-doped crystals (MgO:LiNbO3) are used. They have a higher Laser Damage Threshold. At the same time, the doping has no effect on the optical properties of the crystal.

We can provide doped LN wafers: Er:LN, MgO:LN and Fe:LN with customized doping dose.

Product Parameters

| Material | 3" 4" 6" LN wafer (Optical grade) |
|---------------------------|---|
| Масена | 3 4 0 LN water (Optical grade) |
| Orientation | X & Z |
| Surface finish | single or double side polish (DLP/SLP/SSP/DSP all available) |
| Thickness | 0.18/0.25/0.35/0.50/1.00 mm |
| TTV | <1~5µm |
| BOW | ± (25μm ~40um) |
| Warp | <= 35μm |
| LTV (5mmx5mm) | <1.5 um |
| PLTV(<0.5um) | ≥98% (5mm*5mm) with 2mm edge excluded |
| Curie Temp | 1142°C±3°C |
| Edge | Compl't with SEMI M1.2@with GC800#. regular at C typed |
| Orientation flats | available, per request |
| Doped with | Er:LN, MgO:LN, Fe:LN, Er:MgO:LN |
| Polished side Ra | Roughness Ra<=5A |
| Back Side Criteria | Roughness Ra:0.5-1.0µm GC#1000 |
| Edge Rounding | Compliant with SEMI M1.2 Standard/refer to IEC62276 |
| Cracks, saw marks, stains | None |
| Single Domain | Completed Polarization/Reduced |
| | |

Please contact us for customer specific requirements and questions